


3M

1350F

Flame Retardant Tape with Polyester Film and Acrylic Pressure Sensitive Adhesive

Product Description

3M™ 1350F Tape is an electrical insulating polyester film tape which meets the flame retardancy requirements of UL 510. It consists of materials that are represented in many UL Recognized Insulation Systems and has a UL 130°C temperature rating. It also offers excellent flagging and solvent resistance; good wet grab; smooth, even unwind and is suitable for use on automated equipment.

- **UL Recognized Flame Retardant** 
- **UL Recognized Class 130°C**
- **Non-Diphenyl Oxide Based Flame Retardant**
- **Printable**
- **Solvent Resistant Without Thermosetting**
- **Excellent Shelf Life**
- **Excellent Flagging Resistance**

Colors

3M 1350F Tape is available in Yellow and White. Other Colors on request.

Applications

3M 1350F Tape is especially suited for applications such as wrapping coils, capacitors, wire harnesses, transformers, shaded pole motors and fractional horsepower motors.

UL Component Recognition

UL recognized for use at temperatures not exceeding 130°C and flame retardant per UL Standard 510, UL File Number E17385, Product Category OANZ2. Underwriters Laboratories (UL) Recognized products are evaluated for use as components of end-product equipment that is Listed or Classified by UL. To achieve Underwriters Laboratories Recognition, component construction must meet UL specifications and conditions of acceptability for proper and safe use of the component products.

1350F Flame Retardant Tape with Polyester Film and Acrylic Pressure Sensitive Adhesive

Typical Properties*	1 mil Film	2 mil Film
Adhesive	Acrylic	Acrylic
Backing	Polyester Film	Polyester Film
Backing Thickness ¹	One mil (25 micron)	Two mils (50 micron)
Total Thickness	2.5 mils / 0,063 mm	3.3 mils / 0,083 mm
Colors - Designation	Y,W	Y,W
Temperature Class	130°C (266°F)	130°C (266°F)
Dielectric Breakdown ¹	5500 Volts	7,000 Volts
Insulation Resistance ¹ (megohms)	>1 x 10 ⁶	>1 x 10 ⁶
Breaking Strength ¹	25 lbs/in (44N/10mm)	50 lbs/in (88N/10mm)
Elongation ¹ (% at break)	75	110
Electrolytic Corrosion Factor ³	1.0	1.0
Adhesion to Steel ¹	30 oz/in (3,3N/10mm)	30 oz/in (3,3N/10mm)
UL 510 Flame Retardant ²	Yes	Yes
Printable	Yes	Yes

Note: Typical properties are not recommended for specification purposes. Product specifications will be provided upon request.

Footnote:

¹Test method ASTM D 1000

²UL-recognized for flame retardancy per UL510, Product Category OANZ2, File E17385.

³3M Test Method-Available on request.

Important Notice

All statements, technical information, and recommendations related to Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized officer of Seller. The statements contained herein are made in lieu of

all warranties, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY, INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY, FOR ANY INJURY OR FOR ANY DIRECT OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS THAT WERE DEFECTIVE.



Electrical Specialties Division

6801 River Place Blvd.
Austin, TX 78726-9000
800/328-1368



40% Pre-consumer waste paper
10% Post-consumer waste paper

Litho in USA.

© 3M 2003