



Technical Data Sheet
Version 6
Date : 08-12-2003

M1120 white permanent tape

M1120 is a white polyester tape for thermal transfer printing. It is formulated with a permanent acrylic adhesive and is mainly used for inventory marking as well as for adhesion onto rough surfaces. It can be recommended for outdoor usage.
This tape is halogen free.

Property	Unit	Value	Test method
1. General			
- Total thickness	Micron	135 ± 10%	Micrometer
- Thickness tape	Micron	50 ± 10%	
- Thickness liner	Micron	55 ± 10%	
2. Adhesive properties			
	N/25mm	Dwell 24 hrs 72 hrs	PSTC-1 (modified for 72 hours)
- to stainless steel		22 35	
- to glass		20 40	
- to PVC		18 36	
- to powder coated steel		19 35	
- to wood		13 24	
- to polypropylene film		15 17	
- to polyethylene		10 12	
- to Lever Arch File		8 15	
- to steel computer casing		9 15	
- to textured ABS		22 38	
3. Chemical resistance of text printed in ILP219			
- Eurosuper	30x	No visible effect	Crockmeter, 900g weight/arm
- Diesel	30x	No visible effect	
- Isopropylalcohol	30x	No visible effect	
- Ethanol	30x	No visible effect	
- Ethyl acetate	5x	Printing gone	
- Skydrol* LD-4 (hydraulic engine oil)	30x	No visible effect	
- Sabesto** (brake fluid cleaner)	30x	No visible effect	
- Water	30 x	No visible effect	

Abrasion resistance of text printed in ILP219 - Pencil erasure - Polystyrene pin - Sandpaper	30x 30x 30x	No visible effect No visible effect Moderate print removal	
4. UV light stability of label 30 days with UV light in suntester		No visible effect on text and background	
5. UV light stability of adhesive 30 days with UV light in suntester		No loss of adhesive properties.	
6. Temperature stability - Application temperature - Long term high service temperature - 30 days at 90°C - 30 days at 120°C - Long term low service temperature - 30 days at –18°C - Short term high service temperature - 5' exposure	°C	Room temperature No visible effect No visible effect No visible effect No visible effect No visible effect to tape up to 170°C ; slight shrinkage of tape at 180°C ; moderate shrinkage of tape at 210°C but tape still legible and functional	
7. Humidity resistance of label - 30 days at 40°C, 95 % R.H.		No visible effect on text and background.	
8. Weatherability in QUV with rain/sun cycles - 30 days at 60°C		No visible effect on text. Slight yellowing of background	
9. Adhesion onto rough surfaces - 30 days on computer housing		No loss of adhesive properties.	

10. Shelf life of cassette		1 year at 5-25°C and 40-80% relative humidity in its original packaging. We are confident that our product will perform well beyond this time frame. However, it remains the responsibility of the user to assess the risk of using such product. We encourage customers to develop functional testing protocols that will qualify a product's fitness for use, in their actual applications.
-----------------------------------	--	---

**Skydrol is a registered trademark from Solutia*

*** Sabesto is a registered trademark from Wurth*

Scratch & Solvent resistance : The printed labels are subjected to different scratching sources and chemicals for a fixed number of cycles with a finger weight of 900g.